



ASTON SERVICES

CERTIFICATE OF TESTING

weber sbd 5 Star Grout SP : Batch No.180401/FW59

<u>Test</u>	<u>Results</u>
Water content : 4.8 litres/25 kg bag	
1. Flow cone (ASTM C939)	
At 20°C	
(i) 1 Litre	20.0 secs, 20.0 secs
(i) 1.75 Litres	34.0 secs, 35.0 secs
2. Compressive Strength* at 20°C (BS 1881, 100 mm cubes, wet cured)	
(i) 1 day	38.0 N/mm ²
(ii) 3 days	54.0 N/mm ²
(iii) 7 days	66.0 N/mm ²
(iv) 28 days	74.0 N/mm ²
(v) 90 days	82.0 N/mm ²
(vi) 180 days	94.5 N/mm ²
(vii) 360 days	100.0 N/mm ²
* Average of 2 cubes per age	
3. Expansion test (ASTM C827)	1.64 %

For and on behalf of Aston Services Signed... <i>M. Sadegzadeh</i> ... Date... <i>18.17.02</i> Dr.M.Sadegzadeh, BSc MBA PhD CEng MICE	Genuine Reports Are Embossed Here
---	---