




Compressive strength gain of Five Star Grout SP at lower temperatures

Temperature = 5°C Batch number = 211204 FW77				
1 day	4 days	7 days	14 days	28 days
12.10	51.73	57.49	65.44	72.65
13.16	53.56	60.41	66.63	67.90
12.63	52.65	58.95	66.04	70.28





Compressive strength gain of Five Star Grout SP at lower temperatures

Temperature = 10°C Batch number = 211204 FW77				
1 day	4 days	7 days	14 days	28 days
9.01	43.79	63.1	70.25	82.87
7.49	46.45	64.08	70.24	81.21
8.25	45.12	63.6	70.25	82.04

