




Compressive strength gain of Five Star Grout at lower temperatures


Temperature = 5°C Batch number = 170507 FW34			
1 day	3 days	7 days	28 Days
0	11.3	22.55	36.24
0.1	10.2	19.95	35.88
0.1	10.75	21.25	36.06





Compressive strength gain of Five Star Grout at lower temperatures

Temperature = 10°C Batch number = 170507 FW34			
1 day	3 days	7 days	28 days
3.8	14.53	29.33	44.56
4.2	14.88	28.01	49.22
4.0	14.71	28.67	46.89





Compressive strength gain of Five Star Grout at lower temperatures

Temperature = 20°C Batch number = 170507 FW34			
1 day	3 days	7 days	28 days
12.2	21.88	46.51	56.3
13.54	25.6	45.08	58.21
14.74	23.74	45.8	57.23

